

Elastic additive

Elastifizierungsmittel

D101



Shelf life: 36 months

Color: transparent

Pack: 0,5 l

Properties

Elastic additive D101 serves as an elasticity improver for ground and clear coatings when applied on plastics.

Usage tips

Addition of Elastic additive D101 requires recalculation of the hardener and thinner amounts (see table "Mixing ratio"). Drying time at 20 °C may increase.

Mixing ratio									
		UHS Primer W-W D505		UHS Primer D541		UHS Primer Filler D551		HS Clear coat D323/ HS Clear quick D355	
		By volume, ml	By weight, g	By volume, ml	By weight, g	By volume, ml	By weight, g	By volume, ml	By weight, g
		Coating	100	100	100	100	100	100	100
HS Hardener D220 or HS Hardener fast D222*	28	19	30	18	25	14	60*	60*	
Uni Thinner D110	28	19	30	18	25	14	12	12	
Elastic additive D101	10	7	20	12	20	12	20	20	

* HS Hardener fast D222 is not suitable for curing of the clear coats.