BlenderBlender



Shelf life: 24 months Pack: 0,5 l EU/2004/42 Cat II B(e) VOC820 g/l (VOC limit 840 g/l)

Properties

Blender D117 is a product specially designed for spot repairs. Blender D117 helps to attain the proper orientation of the effect pigments and thus decreases the color differences between original and the new coating.

Usage tips

Application of the Blender D117 should be made in a single layer before the basecoat on the properly pretreated surface. This layer must overlap the repaired surface. After short exposure time the basecoat could be applied. Each further layer of the basecoat must overlap the previous.



Blender Blender

	Substrates			
	The repaired surface must be properly degreased and sanded with P400-500, the zone of the overlapping should be sanded with P800-1000 or with gray sanding pad, then blown off and degreased again.			
	Mixing ratio	By volume		
	Blender D117	100 ml		
	Uni Thinner D110	30 ml		
	Viscosity (DIN 4, at 20 °C)			
s	16 sec			
	Application	Gun tip	Pressure	
>> 	Gravity gun	1,3-1,4 mm	3-4 bar	
HVLP	HVLP gravity gun	1,3-1,4 mm	2 bar	
	Number of coat	1		
	Recommended thickness	15 microns		
	Flash-off time (at 20 °C)			
\frac{\frac{1}{1}\frac{1}\frac{1}\frac{1}{1}\frac{1}{1}\frac{1}{1}\frac{1}{1}\frac{1}{1}\frac{1}{1}\frac{1}{1}\frac{1}{1}\frac{1}{1}\frac{1}{1}\frac{1}{1}\frac{1}\frac{1}{1}\frac{1}{1}\frac{1}\frac{1}{1}\frac{1}{1}\frac{1}{1}\frac{1}\frac{1}{1}\frac{1}{1}\frac{1}{1}\frac{1}\frac{1}{1}\frac{1}{1}\frac{1}\frac{1}{1}\frac{1}\frac{1}\frac{1}\frac{1}{1}\f	3-5 min			
	Drying time (at 20 °C)			
	10-15 min			